VANDENHAUTE J.

Process DUPLICAAT

N° 14,278



A.D. 1899

Date of Application, 11th July, 1899 Complete Specification Left, 23rd Mar., 1800—Accepted, 11th July, 1900

PROVISIONAL SPECIFICATION.

Improvements in the Treatment of Sulphide Ores.

We, JAMES SWINDURNE, of 82, Victoria Street, London, S.W., Engineer, and EDGAR ARTHUE ASDICTOR of same address, Metallurgist, do hereby declare the nature of this invention to be as follows:—

Our invention has reference to the treatment of sulphide ores or products with 5 chlorine, for the purpose of separating the valuable from the worthless constituents, and the resulting metallic chlorides may be electrolysed so as to constitute a cyclic process.

The process is applicable to various sulphides but we will describe it specially

in connection with mixed lead-zinc sulphide ores.

The ore is ground finely, and it is made into a cream with fused chloride of zine, or preferably a mixture of chloride of zine with sodium or potassium chloride. The cream is put into a converter of special design in which it is treated with chlorine, the gas being forced in at the bottom (in a manner similar to the converier used for treatment of copper and other ores or mattes by air blast). 15 At a suitable temperature the chlorine is rapidly absorbed by the metals and sulphur is given off in its place. The re-action is most vigorous at a high temperature and being exothermic the temperature may be regulated by increasing or decreasing the blast of chlorine. If desired, the operation may be pushed so far as to more or less completely volatilize the zinc and the other metallic chlorides 20 leaving the gangue behind as a residue, associated only with small quantities of chlorides. To start the operation it is most convenient to fuse the chlorides cte., in a separate vessel or furnace. The treatment is carried on till all or nearly all the sulphides are converted into chlorides, and the iron which is practically always present, may also be all converted into the ferric state and in this state it is readily precipitated as Fe₂ (), by the addition of ZnO (roasted zinc ore) to the pot. During nearly the whole of the process the chlorine is completely absorbed, sulphur, (and at certain temperatures sulphur chloride) being liberated. These are collected and condensed. Towards the end a little excess of chlorine may be necessary to make sure of oxidizing all the iron to the ferric state. Any chlorine that passes over at this stage may be returned to the chlorine store after condensation of the sulphur. The sulphur is comparatively pure and may be sold for any common purpose. If it is associated with important quantities of metallic chlorides, as will be the case when conducting the process at high temperatures the chlorides may be dissolved in water, leaving the insoluble sulphur behind.

35 At the end of the treatment the converter contains varying quantities of fused chlorides of zinc lead, silver and iron and all the gangue. If zinc oxide has been added to the charge the iron is all present as ferric oxide and the gaugue and the iron may now be allowed to settle, preferably in a separate vessel or furnace, and the clear chlorides poured off. The fused chlorides may then be treated with 40 metallic lead or zinc which removes all the metals which will part with their

BEST AVAILABLE COPY

[Price 8d.]

Swinburne and Ashcroft's Improvements in the Treatment of Sulphide Orcs.

chlorine to lead, such as silver and gold and antimony. The lead which is now rich in silver, and in some cases gold, may be then run off to be treated for the precious metals. The fused chlorides may then be treated with zinc, which takes out the lead by substitution. The fused mass then contains zinc, and potassium chlorides and some trace of chlorides of manganese and other metals of the mixed chlorides may be electrolysed without previous treatment with lead and zinc in which case the silver-lead and zinc will separate progressively and may be drawn off from the electrolysis bath at suitable intervals in a more or less divided state. Instead of precipitating the iron when the charge is in the converter, the fused chlorides may be dissoived in water and the solution treated to for the removal of iron, by means of zinc oxide or otherwise, the iron being brought to the ferric state by chlorine. The resulting solution of zinc and solium or potassium chloride is then evaporated down and fused, and electrolysed to extract the zinc with or without the previous precipitation of silver by lead and lead by zinc, as above described. The double chlorides of sodium or potassium 15 and zinc are preferred because they decompose little on drying and are very fusible. They also fume but little on melting and exposure to the nir.

As to the mixture of gangue and fused chlorides from which the clear chlorides have been described as having been poured off or partially distilled off, the cream may be treated with lead and then with zine in the same way as the clear 20 chlorides. On dissolving in water there will be found some small globules of lead or zine which have been mixed with the gangue; but they are easily separated under water. Or the chlorides may be distilled from the gangue by heating. The more or less pure product of Nnk.Cl. resulting from the above operations is conveniently treated by electrolysis in the fused state, the resulting zine may be 25 collected as molten metal and the chlorine drawn off to be used for the converters. The electrolysis is best carried on in a vat which is heated and kept hot by the electric current, which causes the decomposition of the chloride: the volts necessary at the terminals of the bath will depend to a large extent on the means employed to conserve the heat in the bath. With large vats from 2.5 to 5 volts 30 will be required.

The chlorine from the electrolysis vat may be pumped direct to the converter, but preferably it is cooled and compressed and stored in the liquid state. The storage may be assisted by cooling to a low temperature such as—10° C.

This converter method of treating sulphides with chlorine is applicable to other 35 sulphides, such as iron, copper, nickel, cobalt, antimony etc. In the case of iron pyrites ores particularly, these ores can be treated in conjunction with exidised zinc ores. The sulphur is first expelled and the iron chloride raised to the ferric state by chlorine. The iron is then precipitated as Fe₂ O₃ by the addition of exidised zinc ore. The resulting zinc chloride is then removed and electrolysed as before. The residue of ferric exide may also constitute a valuable product as iron ore or paint.

An operation analogous to the above may be carried on by placing the cream in a revolving furnace of form similar to a Bruckner roasting cylinder, contracted at the ends. The gas is admitted through a pipe leading into the centre door 45 and the sulphur distils off through a similar pipe in the other end door. The doors can be removed and a movable fire box and flue substituted to heat the charge initially.

Dated this 11th day of July 1899.

JAMES SWINBURNE, EDGAR A. ASHCROFT.

Eng Cour man in a Oi Chlorie etitu stitu 10 TI meta conn Brok In 15 crean potas it is tem; Jueta. 20 temp. the te blast

COMID

behin

the o

on til .

of sui

residu 80 chlori

also 11

really Mangi

Zine a

desiret insteachan

the chi

pletely.

nxidisi | stage |

taking

from c and ma quantit at high insolub the en-

35 the pr

40 Towar

25 furna

50

20

1 45

50

Swinburne and Ashcroffe Improvements in the Treatment of Sulphide Ores.

COMPLETE SPECIFICATION.

Improvements in the Treatment of Sulphide Ores.

We, JAMES SWINDERE, Engineer, and EDGAR ARTHUR ASHCHOFF, Mining Engineer, both of Grosvenor Mansions, 82, Victoria Street. Westminster, in the County of London, do hereby declare the nature of this invention and in what manner the same is to be performed to be particularly described and ascertained in and by the following statement:—

Our invention has reference to the treatment of sulphide cres or products with chlorine, for the purpose of separating the valuable from the worthless constituents, and the resulting metallic chlorides may be electrolysed so us to constitute a cyclic process.

The process is applicable to the numerous sulphide ores in which the various metals are contained single or together, but we will describe it particularly in connection with mixed lead-sine silver sulphide ores, such as the well known

Broken Hill ores. In carrying this invention into effect, the ore is crushed and it is made into a 15 cream with fused chloride of zinc, or a mixture of chloride of zinc with sodium or potassium chloride. The creum is put juto a converter or suitable vessel in which it is treated with chlorine, the gas being forced in at the bottom. At a suitable temperature for instance a low red heat, the chlorine is rapidly absorbed by the metals and sulphur is given off in its place. The reaction is most vigorous at high temperatures well above the fusing point of sinc chloride, and being exothermic, the temperature may be maintained and regulated by increasing or decreasing the blast of chlorine. If desired the operation may be pushed so far as to more or less completely volatilize the zinc and the other metallic chlorides, leaving the gangue behind as a residue, associated only with small quantities of chlorides. To start 25 furnace, the converter being heated by internal action. The treatment is carried the operation it is convenient to fuse the chlorides etc. in a separate vessel or on till all or nearly all the sulphides are converted into chlorides. Fresh supplies of sulphides are added to the converter and the operation is corried on until the residual gangue has accumulated so as to make the mixture with the remaining chloride too thick for working. The iron which is practically always present, may also be all converted into the ferric state by chlorine, and in this state it is really precipitated as Fe, O, by the addition of ZnO (roasted zinc ore) to the pot. Manganese is also precipitated as oxide by passing in chlorine in the presence of zinc oxide. Or manganese and iron are both precipitated by blowing in air in the presence of zinc oxide. This zinc oxide may be made from the sulphide if

desired by oxidising a portion of the sulphur of the ore by means of the air blast instead of carrying the decomposition of the sulphide to completion by means of the chlorine blast. During nearly the whole of the process the chlorine is completely absorbed, sulphur being liberated. This is collected and condensed. Towards the end a little excess of chlorine may be necessary to make sure of oxidising all the iron to the ferric state. Any chlorine that passes over at this stage may be returned to the chlorine store after condensation of the sulphur, taking care to avoid the formation of chloride of sulphur by keeping the chlorine from coming into contact with the sulphur. The sulphur is comparatively pure and may be sold for any common purpose. If it is associated with important quantities of metallic chlorides, as will be the case when conducting the process at high temperatures, the chlorides may be dissolved in water, leaving the insoluble sulphur behind, or they may be separated by fractional distillation. At the end of the treatment the converter contains varying quantities of fused

Nº 14,278._A.D. 1899.

Swinburns and Ashcroft's Improvements in the Treatment of Sulphide Oces.

chlorides of zinc lead, silver, iron and manganese and all the gangue. If zinc oxide has been added to the charge the iron and manganese are present as oxides, the gaugue and the iron and manganese oxides may be allowed to settle, preferably in a separate vessel or furnace, and the other chlorides poured off. The fused chlorides may then be treated with metallic lead, which removes all the 5 metals which will part with their chlorine to lead, such as silver and gold and antimony. The excess lead, which is now rich in silver, and in some cases gold, may be then run off to be treated for the precious metals. The fused chlorides may then be treated with zinc, which takes out the lead by substitution. The fused mass then contains sinc chloride or sinc and sodium or potassium chlorides and 10 some traces of chlorides of iron and manganese and other metals. Or the mixed chlorides may be fractionally electrolysed without precious treatment with lead or zinc, in which case the silver-lead and the zinc will separate progressively and may be drawn off from the electrolysis bath at suitable intervals. Instead of precipitating the iron and manganese when the charge is fused, the chlorides 15 after the extraction of lead and precious metals, may be dissolved in water and the solution treated for the removal of iron and manganese by means of zinc oxide or otherwise, the iron being brought to the ferric state by chlorine. The resulting solution of zinc chloride or sinc and sodium or potassium chlorides is then evaporated down and fused and electrolysed to extract the zinc. The 20 double chlorides of sodium or potassium and zinc are preferred for electrolysis because they decompose little on drying and are more fusible and conduct better. They also fume but little on melting and exposure to the air. They also fume but little on melting and exposure to the air. But simple chloride of zinc is preferred in the converter. As to the mixture of gangue and fused chlorides from which the clear chlorides have been poured off or partially 25 distilled off, the cream may be treated with lead and then with zinc in the same way as the clear chlorides. The zinc chloride or the zinc and potassium or sodium chlorides may be dissolved out in water, when some small globules of lead or zinc which have been mixed with the gangue, and which are easily separated under water may be observed. Or the chlorides may be distilled from the gangue 30 by heating. The more or less pure product of zinc chloride resulting from the above operations is conveniently treated by electrolysis in the fused state, the resulting zinc may be collected as molten metal and the chlorine drawn off to be used for the converters. The electrolysis is best carried on in a vat which is heated and kept hot by the electric current which causes the decomposition of the 35 chloride; the pressure necessary at the terminals of the bath will depend to a large extent on the means employed to conserve the heat in the bath.

The chlorine from the electrolysis vst may be pumped direct to the converter, but preferably it is cooled and compressed, and stored in the liquid state. The storage may be assisted by cooling to a low temperature. This converter method 40 of treating sulphides with chlorine is applicable to the treatment of other sulphides and the converter method and the converter method and the converter method and the converter method are the converter method and the converter method and the converter method are the converter method and the converter method are the converter method and the converter method and the converter method are converted as a converter method and the converter method and converter method and converter method are converted and the converter method and converter method and converter method are converted as a converted method and c

phides, such as iron, copper, nickel, cobalt, antimony etc.

Having now particularly described and ascertained the nature of our said invention and in what manner the same is to be performed, we declare that what we claim is:—

1. Treating sulphide ores, suspended in or mixed with a fused chloride or chlorides with chlorine, substantially as described.

2. Treating metallic sulphides with a fused chloride or chlorides and passing chlorine through the mixture, substantially as described.

3. Obtaining sulphur from sulphide ores by passing chlorine through a mixture 50 of the ore and a fused salt, substantially as described.

4. Treating ore mixed with chloride in a converter heated essentially by the chemical action of the chlorine.

5. The cyclic process of treating ores suspended in fused salt with chlorine and electrolytically decomposing the resulting chlorides into metal and chlorine. As

Swin

6. As treated c described

Dat

Redl

18/05 '08 WOW 13:30 [TTY/DY NO 5050]

Nº 14,278.—A.D. 1899.

5

Swinburne and Ashcroft's Improvements in the Treatment of Sulphide Ores.

6. As a step in the herein described process, separating from the fused chloring treated charge, iron and manganese, by precipitation as oxide substantially as described.

Dated this 23rd day of March 1900.

-10

1.5

20

25

30

35

4.5

50

بر:

EDGAR A. ASHCROFT. Boult, Wade & Kilburn, Agents for the Applicants.

Redhill: Printed for Her Majesty's Stationery Office, by Malcomson & Co., Ltd.—1900.

18/05 '98 MON 13-20 FTY/RY NO 50501

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:
☐ BLACK BORDERS
☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
☐ FADED TEXT OR DRAWING
☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
☐ SKEWED/SLANTED IMAGES
☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
GRAY SCALE DOCUMENTS
☐ LINES OR MARKS ON ORIGINAL DOCUMENT
☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.